



COATING

PRODUCT DATA
NMI 680152.

PRODUCT DESCRIPTION:

ONE COMPONENT BACKING EPOXYESTER MELAMINE PRIMER COAT NMI680152.

NMI 680152: is designed for use as a gloss high reflectance primer coat base on epoxyester resin and organic/inorganic pigment with good reflectance efficiency in direct exposure of light.

NMI 680152: can be applied as an inhibitive primer on blasted steel structure and Galvanized suraced.

Standard color availability: Manufactured Ral color.

GENERAL PROPERTIES:

Adhesion:	-Good to both grit blasted and manually prepared surfaces.
Corrosion Resistance	-
Temperature resistance:	-Dry: Maximum 160 °C

PHYSICAL PROPERTIES:

Colors/Shade No	Ral No.
Finish	Flat.
Volume Solid	55 %
Theoretical spreading rate	13.8 m ² /liter 40 Mic. Dft.
Flash point	45 °C
Specific gravity	1.4-1.5 kg/liter
V.O.C.	Max. 360 gr/liter
Shelf life	6 month (25°C / 77°F) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

APPLICATION :

Conditions	Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3 °C above the dew point.		
Method	Airless sprays	Air spray	Brush (touch-up)
Thinner (max. vol.)	30006(10-20%)	30006(25%)	30006 (5%)
Spray setting			
Pump ratio minimum	30:1		
Tip size	.021"	1.8 mm	
Tip pressure	150 bar / 2200 Psi	4 – 5 bar	
	(Airless spray data are indicative and subject to adjustment)		
Cleaning of tools	Thinner:NMI 30006		
Indicated film thickness, dry	55 microns		
Indicated film thickness, wet	100 microns		

Issued:

Sep. 2018

DRYING AND CURING TIMES AT (20°C):

Flash off	10-15 min
Time for Backing	15-20 min
Temperature for Avene	140-160°C
Recoat interval, min	8 hours
Recoat interval, max	None , see REMARKS

SURFACE PREPARATION:

Primed steel	Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning.
Maintenance	Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Remove all rust and loose material by abrasive blasting or power tool cleaning. Dust off residues.

EMARKS:

PRECEDING COAT:	None.
SUBSEQUENT COAT:	None.
Film thickness:	May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and recoating intervals. Normal range is 30-40 microns/ 1.2-1.6 mils.
Thinning:	The type and amount of thinner depend on application conditions, application method, temperature, ventilation, and substrate. Thinner 30006 is recommended in general.
Recoating And drying/curing Time	

Physical data versus temperatures in mild atmosphere:					
Surface temperature	5°C/41°F	10°C/50°F	20°C/68°F	30°C/86°F	
Dry to touch approx.	20 hours	10 hours	6 hours	4 hours	
Resist condensing humidity/ light showers after	4 days	2 days	48 hours	24 hours	
Fully cured	20 days	14 days	15 days	10 days	
Recoating interval with alkyd finish	Min	24 hours	16 hours	8 hours	6 hours
	Max	None	None	None	None

A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

SAFETY:

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult RSI material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

Issued : Sep 2016

NMI Paint Co.

Product data sheet 680152.